

Cito Primer 09

Product description

Type

It is a Pliolite solvent-based primer.

Features and benefits

Provides excellent water and alkali resistance. Provide good penetration and adhesion.

Recommended use

Specially formulated as a sealer or a primer on exterior surfaces. Especially for flex topcoat.

Substrate

On concrete, cement plaster and masonry surfaces.

Product data

Packaging size	5 L and 20L Packing may vary from country to country according to local requirements.
Colours	Transparent or White
Solids	25 ± 2 volume%
Flash point	Closed cup: 28°C (82,4°F)

Application data

Remarks

Handle with care. Stir well before use.

Application methods

By brush, roller, airless spray or conventional spray.

Guiding data for airless spray

Nozzle tip	0.018-0.021"
Spray angle degrees	65° - 85°
Pressure at nozzle	150 Kg/cm ² (2100 psi)

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Recommended film thickness per coat

Dry	Minimum	30 µm
Dry	Maximum	40 µm
Wet	Minimum	120 µm
Wet	Maximum	160 µm

Film thickness will vary and is calculated as average.

Spreading rate per coat

Theoretical Spreading rate per coat (m²/l) : 6.3 - 8.3

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Thinner

Jotun Thinner No. 7

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

The given data must be considered as guidelines only. The actual drying time and time before recoating may be shorter or longer, depending on the ambient temperature, film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

Relative Humidity (RH)	50 %	50 %	50 %
Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	2 h	1 h	30 min
Hard dry	12 h	5 h	3.5 h
Dried to over coat, minimum	12 h	5 h	3.5 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of foam release agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Primer

Cito Primer 09 :1 Coat(s)

Topcoat

Strax Matt (C) or Majestic Royale Matt or Jotashield Tex Profile or Pioneer 200 Matt : 2 Coat(s)

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Cito Primer 09

24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Tests

JG/T 210-2007 Primer for interior and exterior wall.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health- and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.